

FUZEICE®



- Easy Application with 2 In 1 Applicator/Spreader
- High Thermal Conductivity and High-Efficiency
 Heat Transfer, Allowing for Higher Clock Speeds

FUZEICE®

Thermal Conductivity 11.25 W/mK

Thermal Conductivity	11.25 W/mK
Thermal Resistance	0.07 cm² K/W @ 60 PSI
Viscosity	56000 poise
Density	2.6 g / cm³
Volume Resistivity	1.8 x 10 ¹² Ω
Storage Temperature	5 °C to 25 °C
Temperature	-50 °C to 200 °C
Net Weight	3.5 g / 0.13 oz 7 g / 0.25 oz

